

EFFECTS OF IONIC COMPOUNDS ON OPTIMIZATION OF PHYSICOCHEMICAL PROPERTIES OF BIOPOLYMER ISOLATED FROM PAKISTANI WATER CHESTNUTS

Zubala Lutfi*¹, Anjum Nawab¹, Feroz Alam¹, Mohib Reza² and Abid Hasnain¹

¹Department of Food Science and Technology, University of Karachi, Karachi-75270, Pakistan
anjumnawab@uok.edu.pk; ferozalam@uok.edu.pk; abidhasnain@uok.edu.pk

²Department of Applied Chemistry and Chemical Technology, University of Karachi, Karachi-75270, Pakistan;
E-mail: mrkazmi@uok.edu.pk

*Corresponding author: E-mail: zubala.lutfi@uok.edu.pk; Tel: +92-324-2013186; Fax no: +92-21-99243206

ABSTRACT

The purpose of this study was to examine the physicochemical properties of biopolymer extracted from water chestnut in the presence of different ionic compounds (KCl, Na₂HPO₄, CaCl₂) at fixed starch (5%) and salts (1%) concentration. Experimental results showed that the presence of CaCl₂ had a significant impact on swelling and thermal properties of water chestnut starch. The onset temperature of starch was found to be increased in the presence of KCl and CaCl₂, whereas a reverse trend was observed in case of Na₂HPO₄. Furthermore, the addition of salts drastically reduced the swelling power and water absorption of water chestnut starch. The increase in peak viscosity and retrogradation was noticed after the addition of Na₂HPO₄ and CaCl₂, respectively.

Key-words: Biopolymer, Viscoamylograph, Differential Sensory Calorimeter, Swelling Power

INTRODUCTION

Recently, the use of biodegradable polymers have been increasing in many applications such as in agriculture, biomedical, forestry, medicines, wild life conservation and waste management. Starch due to naturally occurring and readily available obtained from different sources such as wheat, rice, tapioca etc, is used extensively in food as well as non-food applications.

Water chestnut starch is underutilized by the food industry because of limited understanding of its modifications and uses. It is cheap and has sufficient starch content which is promising in itself. The edible region of water chestnut is rich in starch and composed of thin walled storage parenchyma quite similar to potato starch in appearance and has vascular strands in between. It maintains a crunchy and firm texture after cooking and long heat treatment which was commendable and was unlike what is seen in case of conventional starches such as potato and rice (Singh *et al.*, 2011). Water chestnut is a good contender for utilization in food and related industries owing to its large starch reserves.

Salt is a common additive in starch based products for improving organoleptic properties of the product. The most common salt additives are sodium chloride and calcium chloride (Albarracín *et al.*, 2011). Addition of sodium chloride has shown increase in gelatinization temperature of tapioca starch and retrogradation time of the starch gel upon cooling (Chuang *et al.*, 2017). Various salts have been tried and their effects on potato starch have been documented (Wang *et al.*, 2016).

It was imperative that due attention was given to characterization of water chestnut starch. This would allow for its utilization in the industry and also customize its properties through physical and chemical modifications to suit specific requirements and applications. Eventually it will raise the economic status of people as well (Lutfi *et al.*, 2017b). Water chestnut starch has not been subject to much study especially in the area of interaction with various salts. If the said study is conducted it could open new avenues for tailoring the water chestnut starch to suit myriad of applications. It is an exploitable source thus making it a good study candidate. Therefore, the main purpose of this experiment was to observe the effects on physicochemical, swelling and thermal properties of biopolymer (starch) extracted from Pakistani water chestnuts in the presence of Ions.

MATERIALS AND METHODS

Materials

The water chestnuts were obtained in dried form from the local market of Karachi, Pakistan. The extraction of starch was done according to the method reported previously by our group (Lutfi *et al.*, 2017a). Analytical grade

calcium chloride (CaCl₂), potassium chloride (KCl) and sodium dihydrogen phosphate (Na₂HPO₄) were provided by Sigma-Aldrich Co. (St. Louis, MO). The moisture, protein, fat, ash and total amylose content of extracted starch was found to be 8.5, 0.1, 0.19, 0.17 and 28.5%, respectively (Lutfi *et al.*, 2017b).

Methods

Swelling Capacity and Solubility

The evaluation of swelling power and solubility were performed according to the method of (Waliszewski *et al.*, 2003) with slight modifications. The water chestnut starch (1% w/w) was dispersed in solution containing salts (1% w/w). The samples were poured into the screw cap graduated centrifuge tubes. These tubes were then placed in shaking water bath for 30 mins, while maintaining the temperature of 90 °C. Then, the tubes were immediately put in chilled water and allowed to cool to room temperature. After cooling, the samples were centrifuged at 3000 x g for 15 mins and then the supernatant were dried at 130 °C for 24 h. Swelling capacity was calculated as

$$\text{Swelling capacity (g/g)} = \frac{\text{Wet precipitated paste}}{\text{Dry weight}}$$

$$\text{Solubility (\%)} = \frac{\text{Dry precipitated paste}}{\text{Dry weight}} \times 100$$

Transparency

The aqueous suspensions of WCS (1% w/w) with different salts in were kept in water bath maintained at 100°C for 30 min with constant stirring to avoid any lump formation followed by rapid cooling at 35°C. The transmittance (%) of suspensions was measured at 650 nm against water as a blank with spectrophotometer (Beckman DU-650, CA (USA)).

Microviscoamylography

Pasting behavior of 5% (w/w) WCS alone and WCS/salts blends were measured using a Brabender microviscoamylograph (Model 803201, Germany). The samples were heated from 30 to 95 °C with a constant heating rate of 1.5 °C/min and then held at 95 °C for 30 min. The paste was cooled to 50 °C with constant rate and held at this temperature for 10 min.

Thermal properties

Thermal properties of water chestnut alone and water chestnut/salts blends were measured by differential scanning calorimeter (DSC Q10, TA Instruments, USA). In 20 mL aluminum pan, starch and deionized water was added with the help of syringe in the ratio of 1:2. Hermetically sealed aluminum pan is equilibrated for 1 hr and then passed through gelatinization thermal scan at the rate of 10 °C/ min at the temperature range of 30 °C to 120 °C and empty aluminum pan is used as reference.

Universal Analysis software is used for the calculation of onset temperature (To), peak gelatinization temperature (Tp), conclusion temperature (Tc), and enthalpy change (ΔT).

Statistical analysis

Statistical analysis was performed by using SPSS (Version 17.0. Inc, Chicago, USA). The data was evaluated by ANNOVA followed by LSD at p=0.05.

RESULTS AND DISCUSSION

Swelling capacity and Solubility

Swelling capacity is defined as the quantity of water absorbed by the starch granules at elevated temperature. Table 1 shows the results of swelling capacity of water chestnut starch in presence of different salts.

The presence of salts significantly changed the swelling capacity and solubility of water chestnut starch (WCS). In precise words, salts reduced the swelling power of WCS substantially. Equipollent results were obtained with cassava starch when its swelling capacity was tested with and without the addition of salts as reported by Jyothi *et*

al.,(2005). The reason for reduction of swelling power of starch in presence of salts can be explained by citing two reasons. 1) There is an attractive and repulsive interaction between starch and salt ions (Oosten, 1982; Oosten, 1983; Oosten, 1990) and 2). Salts and starch compete for available water. This result in reduction of swelling of starch granules and consequently decreased leaching of amylose.

All salts increased the solubility of water chestnut starch. Solubility of $\text{NaH}_2\text{PO}_4 > \text{CaCl}_2 > \text{KCl}$ was recorded at a temperature of 90 °C. In the report by Zhou *et al.*,(2014), similar results were mentioned and he went on to explain that the monoatomic Cl^- ion which has a large diameter and greater degree of polarization tends to disrupt the hydrogen bonds between starch-starch and starch-water thus leading more water molecules access which further increased the solubility as opposed to native starch. Therefore, such solutes can increase water solubility of native WCS.

Transparency

Transparency of starch paste can be determined by passing the light through it. Many factors affected the transparency such as swelling capacities, amylose and amylopectin ratio, and size of the granules (Singh and Singh, 2003; Sitohy *et al.*, 2000). Table 2 showed the transparency of water chestnut starch pastes in the presence of salts during storage at room temperature. Starch showed significant change in transparency after the treatment with salts.

Sodium dihydrogen phosphate was found to increase the transparency of water chestnut starch. The results were similar to the results from Li *et al.* (2011). On the other hand, no change was observed in the presence of calcium chloride and potassium chloride on the transparency of water chestnut starch.

Table 1. Swelling capacity (g/g) and solubility (%) of Water chestnut starch with different salts.

Sample	Temperatures (°C)	
	Swelling power	Solubility
Control	12.23 ± 0.61	5.7 ± 0.37
KCl	5.67 ± 0.2	16.7 ± 0.35
CaCl_2	5.83 ± 0.31	31.7 ± 0.26
NaH_2PO_4	5.54 ± 0.42	31.7 ± 0.21
LSD _{0.05}	0.15	0.12

Table 2. Transparency of water chestnut starch with different salts.

Samples	Transparency (%)
Control	3.5 ± 1.11
KCl	3.5 ± 1.21
CaCl_2	3.4 ± 2.31
NaH_2PO_4	4.3 ± 1.22
LSD _{0.05}	0.11

Pasting Properties

The effect of salts on the pasting properties of water chestnut starch was determined by Viscoamylograph and is illustrated in the Table 3. The peak viscosity of water chestnut starch was significantly increased after the addition of salts from 72.3 BU to 76 BU and 88 BU for potassium chloride and sodium di hydrogen phosphate respectively. An increase in peak viscosity of water chestnut starch could be due to the influence of interaction between salts (potassium chloride and sodium di hydrogen phosphate) to the proteins and lipids components present in starch. Our results were similar to previous studies conducted by Samutsri and Suphantharika, (2012). In another observation the viscosity of starch was dramatically reduced in presence of calcium chloride at similar concentrations due to the higher ionic strength of calcium chloride as opposed to the other salts tested. Comparable results were reported by Yu *et al.* (2016) for sweet potato starch.

The gelatinization temperature of water chestnut starch was found to be marginally increased in the presence of salts. This result could be confirmed by the observation that the swelling power of water chestnut starch decreased drastically after the addition of salts. Similar results have been observed for potato starch (Chen *et al.*, 2014), rice starch (Samutsri and Suphantharika, 2012), and sago starch (Ahmad *et al.*, 1999a). The theory of limited swelling and gelatinization of starch granules in the presence of salts has been well explained by Oosten (1982). Correspondingly, the altered structure of water and decrement in “free” water for absorption by starch granules have been established as causative factors for suppression of swelling and gelatinization.

In the presence of calcium chloride and sodium dihydrogen phosphate the limited increase in breakdown was observed but it remained unaffected in the presence of potassium chloride. The granules of water chestnut starch become more tightened in the presence of potassium chloride.

Setback viscosity being the measure of reassociative tendency of starch granules. Addition of calcium chloride significantly increased the setback (i.e. amylose retrogradation) of water chestnut starch due to a higher solubility of water chestnut starch (Table 1) that resulted in higher exudation of amylose chains. Similar results were reported for sweet potato starch (Yu *et al.*, 2016). However, negligible reducing effect was observed in the presence of potassium chloride and sodium di hydrogen phosphate.

Table 3. Pasting properties of Water chestnut starch with different salts.

Samples	T _g °C	Pv (BU)	BD (BU)	SB (BU)
Control	77.2 ± 1.1	72.3 ± 3.1	0.0 ± 0.1	25.2 ± 1.3
KCl	76.6 ± 2.1	76 ± 2.2	0 ± 0.2	25 ± 0.5
CaCl ₂	77.8 ± 3.2	67 ± 1.3	1 ± 0.1	57 ± 1.2
NaH ₂ PO ₄	77.4 ± 2.5	88 ± 3.1	2 ± 0.2	22 ± 1.5
LSD _{0.05}	0.42	0.23	0.15	0.24

Table 4. Thermal properties of water chestnut starch with different salts.

Samples	T _o (°C)	T _p (°C)	T _c (°C)	ΔT (T _c - T _o)
Control	63.2 ± 1.1	66.3 ± 3.1	70.1 ± 0.1	6.9 ± 1.2
KCl	66.2 ± 2.3	70.1 ± 4.3	74.2 ± 0.2	8.0 ± 2.4
CaCl ₂	68.8 ± 2.5	72.5 ± 2.3	76.3 ± 0.1	7.5 ± 2.6
NaH ₂ PO ₄	64.4 ± 1.3	68.2 ± 1.2	72.3 ± 0.1	7.9 ± 1.4
LSD _{0.05}	0.18	0.21	0.15	0.18

onset temperature (T_o), peak gelatinization temperature (T_p), conclusion temperature (T_c), and enthalpy change (ΔT).

Thermal Properties

The thermal properties which include onset temperature (T_o), peak temperature (T_p), and conclusion temperature (T_c) gelatinization temperatures, and the gelatinization range (ΔT) of water chestnut starch alone and water chestnut starch with salts were evaluated by DSC, were depicted in Table 4.

The increase in magnitude of T_o , T_p , and T_c and decreased ΔT values of water chestnut starch were observed in the presence of salts at 1 % concentration. It has been reported that the changing pattern of gelatinization and enthalpy of starches in the presence of salts is mainly dependent on the type of salt and their concentration used (Singh and Singh, 2003; Oosten, 1983; Oosten, 1990; Jane, 1993; Ahmad *et al.*, 1999). Previous studies showed that, at low concentration of CaCl_2 , the T_o of corn starch, T_p of sago, wheat, corn, rice were slightly increased (Ahmad *et al.*, 1999; Maaruf *et al.*, 2001; Jane, 1993; Chinachoti *et al.*, 1991) but, these gelatinization temperatures were found to decrease on increasing the concentration of salts up to 1 M. However, some other studies reported that the ΔT of corn starch was continuously increased above 1M for CaCl_2 and when the concentration reached up to 6M the early gelatinization of corn starch was noticed (Samutsri and Suphantharika, 2012). However, the concentration used in this study was quite lower than those reported earlier. In the presence of salts, the mechanism of starch gelatinization was depending on different factors, especially the interaction between solvent and polymer, the structure of water, and the attractive and repulsive interactions between the ions and starch. Oosten (1982 and 1983) explained that the alcoholic groups present in the starch chain is converted into sodium and calcium alcoholate group which could be easily dissociated, resulting a increase in the difference of potential between the water phase and starch granule called Donnan potential.

In this study it was found that the addition of CaCl_2 has more pronounced effect on T_o , T_p , and T_c of water chestnut starch as compared to other salts. Similar results were reported by Ahmad *et al.* (1999) for sago starch. This could be due to the presence of more Cl^- ions per mole of CaCl_2 as compared to KCl.

Conclusion

It was concluded that the addition of different salts markedly affected the pasting and thermal properties of water chestnut starch. Overall reduction in swelling power was observed in the presence of salts. Transparency was found to be increased after the addition of NaH_2PO_4 . The addition of salts in varying proportions to native starch based foods open new avenues in food processing and it modifies the rheology of the starch to give the desired finished product. More research is required in this area to fully understand the potential of this novel source of starch which is a promising new ingredient in food processing.

REFERENCES

- Ahmad, F. B., P. A. Williams, J.-L. Doublier, S. Durand and A. Buleon (1999). Physico-chemical characterisation of sago starch. *Carbohydrate Polymer*, 38(4): 361-370.
- Albarracín, W., I. C. Sánchez, R. Grau and J. M. Barat (2011). Salt in food processing; usage and reduction: a review. *International Journal of Food Science and Technology*, 46(7): 1329-1336.
- Chen, H.-H., Y.-S. Wang, Y. Leng, Y. Zhao and X. Zhao (2014). Effect of NaCl and sugar on physicochemical properties of flaxseed polysaccharide-potato starch complexes. *Journal of Science Asia*, 40(1): 60-68.
- Chinachoti, P., M. Kim-Shin, F. Mari and L. Lo (1991). Gelatinization of wheat starch in the presence of sucrose and sodium chloride: correlation between gelatinization temperature and water mobility as determined by oxygen-17 nuclear magnetic resonance. *Cereal Chemistry*, 68 (3): 245-248.
- Chuang, L., N. Panyoyai, R. A. Shanks and S. Kasapis (2017). Effect of salt on the glass transition of condensed tapioca starch systems. *Journal of Food Chemistry*, 229: 120-126.
- Jane, J. L. (1993). Mechanism of starch gelatinization in neutral salt solutions. *Starch-Stärke*, 45(5): 161-166.
- Jyothi, A. N., K. Sasikiran, M. S. Sajeev, R. Revamma and S. N. Moorthy (2005). Gelatinisation properties of cassava starch in the presence of salts, acids and oxidising agents. *Starch-Stärke*, 57(11): 547-555.
- Li, W., Y. Bai, Q. Zhang, X. Hu and Q. Shen (2011). Effects of potassium alum addition on physicochemical, pasting, thermal and gel texture properties of potato starch. *International Journal of Food Science and Technology*, 46(8): 1621-1627.
- Lutfi, Z., A. Nawab, F. Alam, A. Hasnain and S. Z. Haider (2017a). Influence of xanthan, guar, CMC and gum acacia on functional properties of water chestnut (*Trapa bispinosa*) starch. *International Journal of Biological Macromolecule*, 103: 220-225.
- Lutfi, Z., A. Nawab, F. Alam and A. Hasnain (2017b). Morphological, physicochemical, and pasting properties of modified water chestnut (*Trapa bispinosa*) starch. *International Journal of Food Properties*, 20(5): 1016-1028.

- Maaruf, A., Y. C. Man, B. Asbi, A. Junainah and J. Kennedy (2001). Effect of water content on the gelatinisation temperature of sago starch. *Carbohydrate Polymer*, 46(4): 331-337.
- Oosten, B. J. (1990). Interactions between starch and electrolyte. *Starch-Stärke*, 42 (9): 327-330.
- Oosten, B. J. (1982). Tentative hypothesis to explain how electrolytes affect the gelatinization temperature of starches in water. *Starch-Stärke*, 34(7): 233-239.
- Oosten, B. J. (1983). Explanations for phenomena arising from starch-electrolytes interactions. *Starch-Stärke*, 35(5): 166-169.
- Samutsri, W. and M. Supphantharika (2012). Effect of salts on pasting, thermal, and rheological properties of rice starch in the presence of non-ionic and ionic hydrocolloids. *Carbohydrate polymers*, 87(2): 1559-1568.
- Singh, G. D., C. S. Riar, C. Saini, A. S. Bawa, D. S. Sogi and D. C. Saxena (2011). Indian water chestnut flour-method optimization for preparation, its physicochemical, morphological, pasting properties and its potential in cookies preparation. *LWT- Food Science and Technology*, 44(3): 665-672.
- Singh, J. and N. Singh (2003). Studies on the morphological and rheological properties of granular cold water soluble corn and potato starches. *Journal of Food Hydrocolloids*, 17(1): 63-72.
- Sitohy, M. Z., S. S. El-Saadany, S. M. Labib and M. F. Ramadan (2000). Physicochemical properties of different types of starch phosphate monoesters. *Starch-Stärke*, 52(4): 101-105.
- Waliszewski, K. N., M. A. Aparicio, L. S. A. Bello and J. A. Monroy (2003). Changes of banana starch by chemical and physical modification. *Carbohydrate Polymetr*, 52(3): 237-242.
- Wang, Y., S. H. Bryant, T. Cheng, J. Wang, A. Gindulyte, B. A. Shoemaker, P. A. Thiessen, S. He and J. Zhang (2016). Pubchem bioassay. *Nucleic Acid Research*, 45(D1): D955-D963.
- Yu, S. X., T. H. Mu, M. Zhang and Z. K. Zhao (2016). Effects of inorganic salts on the structural and physicochemical properties of high hydrostatic pressure-gelatinized sweet potato starch. *Starch-Stärke*, 68: 980-988
- Zhou, H., C. Wang, L. Shi, T. Chang, H. Yang and M. Cui (2014). Effects of salts on physicochemical, microstructural and thermal properties of potato starch. *Journal of Food Chemistry*, 156: 137-143.

(Accepted for publication July 2019)